



### Applications

*Putty & Fiber Glass & Many Other Uses*

### Chemical Analysis

<i>Properties</i>	<i>Standard</i>
CaCO <sub>3</sub>	99% Min
Fe <sub>2</sub> O <sub>3</sub>	0.02% Max
Al <sub>2</sub> O <sub>3</sub>	0.03% Max
MgO	0.05% Max
SiO <sub>2</sub>	0.05% Max

### PSD Malvern

<i>Properties</i>	<i>Standard</i>
	Over 500 $\mu$ $\leq$ 0%
	Over 250 $\mu$ $\leq$ 0.5%
	Over 75 $\mu$ between 15 - 25 %

### Physical Properties

<i>Properties</i>	<i>Standard</i>
Brightness	97% Min
Whiteness	98% Min
Density	2.4 – 2.7 g/cm
Hardness	3 Moh
Moisture	0.20%
PH	9

EGYPT,ELMINIA,INDUSTRIAL ZONE

Website

[almadinaalmonaoura.com](http://almadinaalmonaoura.com)

CEO

[ali.farag@almadinaalmonaoura.com](mailto:ali.farag@almadinaalmonaoura.com)

Sales & Export Maneger

[hossam.ali@almadinaalmonaoura.com](mailto:hossam.ali@almadinaalmonaoura.com)

Contacts

01001179526 - 01093630043